



Mapeflex MS45



One-component flexible, thixotropic, quick-hardening silitated polymer-based hybrid sealant and adhesive with a high modulus of elasticity. Also suitable for damp substrates

WHERE TO USE

Mapeflex MS45 has been specifically developed for sealing expansion, fillet and distribution joints on horizontal and vertical surfaces. It is also recommended to form internal and external flexible bonds between similar and dissimilar materials commonly used in the building industry and to replace or integrate mechanical fasteners.

Some application examples

Used as sealant:

- Sealing expansion, fillet and distribution joints subject to movements of up to 20% of the average width of the joint.

It is most frequently used for the following applications:

- traditional façades;
- ventilated façades;
- civil and industrial floors, including those subject to heavy vehicular traffic;
- window and door fittings;
- cracks and splits;
- paintable joints;
- tin roofs and metalwork.

Used as flexible adhesive:

When applied at a thickness of 3 mm, it forms a flexible bond between most building materials, including many types of plastic.

Its high bond strength without primer and its rapid polymerisation make **Mapeflex MS45** easy to use when installing building elements or bonding construction features, both internally and externally.

Bonds on the following:

- cement and cement-based materials;
- bricks;
- steel;
- copper;
- aluminium;
- painted surfaces in general;
- glass and mirrors;
- gypsum;
- wood and wood-based materials;
- ceramic and klinker;
- insulating materials in general;
- many types of plastic.

TECHNICAL CHARACTERISTICS

Mapeflex MS45 is a thixotropic adhesive and sealant made from silitated polymers and thus completely free of silicone and isocyanates.

Compared with polyurethane products, **Mapeflex MS45** is easier to extrude and smooth over (especially when applied at low temperatures), has a wider application temperature range, does not blister even during particularly damp conditions, has a greater compatibility with damp substrates during application, is more resistant to UV rays, hardens more quickly, has a longer shelf life and is available in handy plastic cartridges.

Compared with neutral silicone products, **Mapeflex MS45** forms a better bond on compact and absorbent substrates, drastically reduces the amount of dirt which collects on the surface, offers better mechanical properties such as tensile and shear strength.

Before painting over **Mapeflex MS45** it must be fully polymerised and the paint used must be similar to

Mapeflex MS45



Bonding plastic profiles
on a surface outside

TECHNICAL DATA (typical values)

PRODUCT IDENTITY

Classification according to EN 15651-1:	F-EXT-INT-CC, class 20 HM
Classification according to EN 15651-4:	PW-EXT-INT-CC, class 20 HM
Appearance:	thixotropic paste
Colour:	white and grey (300 ml)
Density (g/cm ³):	1.47 ± 0.07
Dry solids content (%):	100
Brookfield viscosity at +23°C (mPa·s):	1,300,000 ± 200,000 (rotor F - 5 revs)
EMICODE:	EC1 R Plus - very low emission

APPLICATION DATA (at +23°C and 50% R.H.)

Application temperature range:	from +5°C to +35°C
Skin time:	30 minutes
Complete hardening:	3 mm/24 hours - 4.5 mm/48 hours - 8.5 mm/7 days
Set to light foot traffic:	according to the depth of the joint

FINAL PERFORMANCE

Shore A hardness (DIN 53505):	36 ± 3
Tensile strength (ISO 37 type 3) (N/mm ²): - after 28 days at +23°C:	1.85
Elongation at failure (ISO 37 type 3) (%): - after 28 days at +23°C:	500
Resistance to UV rays (ASTM C793):	excellent
In-service temperature range:	from -40°C to +90°C
Elongation in service (continuous service) (%):	20
Modulus of elasticity at +23°C (ISO 8339) (N/mm ²):	0.75
Springback (%):	80

Elastocolor Paint. We recommend carrying out preliminary tests to make sure the sealant and paint are compatible.

Mapeflex MS45 complies with EN 15651-1 ("Sealants for façade elements") with performance rating F-EXT-INT CC and EN 15651-4 ("Sealants for pedestrian walkways") with performance rating PW-EXT-INT-CC.

Mapeflex MS45 contains no solvents, has a very low emission level of volatile organic compounds (EC1R Plus according to the GEV Institute) and is characterised by its high mechanical strength according to ISO 11600 (class F20 HM).

Mapeflex MS45 may also be applied on substrates which are temporarily wet due to unsuitable surrounding conditions (recent rain, contact with water, atmospheric damp, etc.); for continuous capillary rising damp, apply a coat of **Primer FD** beforehand. If applied on damp substrates or on substrates continuously immersed when in service, the mechanical performance of the product could be significantly lower compared with use in dry conditions.

Mapeflex MS45 hardens by reacting with the humidity in the surrounding air without giving significant levels of liquids or gases potentially hazardous for the user or the environment, which is why no safety warnings need to be applied on the packaging. The product is ready to use and is available in plastic cartridges to be used with traditional extrusion guns.

RECOMMENDATIONS

- Do not apply on dusty or crumbling surfaces.
- Do not apply on wet surfaces.
- Do not apply on surfaces with traces of oil, grease and stripping compound otherwise the bond may be compromised.
- Do not apply on bituminous surfaces where there may be traces of bleeding oil.
- Do not apply **Mapeflex MS45** if the temperature is below +5°C.
- Before painting over the sealant make sure it is compatible with the type of paint used.
- Use **Mapeflex MS Crystal** for transparent sealing.

APPLICATION PROCEDURE

Preparation of the surface for bonding or sealing

Surfaces to be bonded or sealed must be clean, dry, sound and free of dust, loose parts, oil, grease, wax and old paintwork. When used for sealing, **Mapeflex MS45** must only bond to the sides of the joint and not to the bottom. Therefore, for joints subject to movement, insert **Mapefoam** compressible, closed-cell, polyethylene cord with a suitable diameter for the width of the joint to regulate the depth of the sealant according to the table below:

WIDTH OF JOINT	DEPTH OF SEALANT
Up to 10 mm	Same as width
From 11 to 20 mm	10 mm in all cases
More than 20 mm	Half the width

Mapeflex MS45 withstands movement when in service of up to 20% of the average width of the sealed joint. If movement is higher than 20% when in service, use **Mapeflex PU40** polyurethane sealant or **Mapesil LM** neutral silicone sealant, both with a low modulus of elasticity.

To avoid the sealant seeping out of the joint and to get a more attractive finish, we recommend applying masking tape along the edges of the joint which should then be removed immediately after smoothing over the surface of the sealant.

Mapeflex MS45 bonds well to most absorbent or compact substrates used in the building industry, as long as they are free of traces of dust and stripping compound. We recommend applying **Primer FD** if absorbent surfaces are not sufficiently solid or compact, or when the joints are subjected to high mechanical stress or frequent, prolonged immersion in water.

If applied on plastic, we recommend using **Primer P** and roughening the surface. Because there is a very wide range of plastics available, we recommend carrying out a preliminary test or contacting the MAPEI Technical Services Department beforehand.

Application of Primer FD or Primer P

Apply the most suitable primer, according to the type of substrate, along the edges of the joints with a brush and wait until it completely dries before extruding the **Mapeflex MS45**.

Preparation and application of Mapeflex MS45 when used for sealing

Insert the cartridge in an extrusion gun, cut the tip of the cartridge, screw on the extrusion nozzle, cut the nozzle at an angle of +45°C and according to the extruded width required and squeeze out the product in a continuous flow into the joint to avoid entrapping air in the joint.

Immediately after extruding the product, smooth over the surface with a tool with a suitable size and shape while keeping it continuously wet with soap and water.

Preparation and application of Mapeflex MS45 when used for flexible bonds

When bonding elements with a small surface area, extrude single drops of the product on the back of the element and press it well down onto the substrate to spread the adhesive uniformly. When bonding elements with a large surface area, extract a series of

Mapeflex MS45



vertical, parallel beads around 10-15 cm apart and press on well to spread the adhesive uniformly.

The bonded element may be adjusted within 20 minutes of laying at a temperature of +23°C. When bonding heavy loads or in critical laying conditions, extra support such as clamps, props etc. may be necessary for the first 24 hours at +23°C.

Do not bond with layers of product more than 3 mm thick.

CONSUMPTION

For sealing:

According to the size of the joint. See consumption table below.

CONSUMPTION TABLE	
Size of joint in mm	Linear metres of product per 300 ml cartridge
5 x 5	12
10 x 10	3
15 x 10	2
20 x 10	1.5
25 x 12.5	0.9
30 x 15	0.6

For bonding:

According to the bonding technique used (spot bonding or with beads).

Cleaning

Mapeflex MS45 may be removed from surfaces, tools, clothing etc. with toluol or alcohol before it hardens. Once hardened, it must be removed mechanically or with Pulicol 2000.

PACKAGING

Boxes of 12 (300 ml cartridges).

COLOURS AVAILABLE

Mapeflex MS45 is available in white, 113 grey, brown.

STORAGE

Mapeflex PU45 may be stored for up to 15 months in its original packaging in a dry, cool place.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Mapeflex MS45 is not considered hazardous according to current standards and regulations regarding the classification of mixtures. It is however recommended to use gloves, eyes protection and to take the usual precaution taken when handling chemical products.

For further and complete information about the safe use of our product please refer to the latest version of our Material Safety Data Sheet.

PRODUCT FOR PROFESSIONAL USE.

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the **Technical Data Sheet**, available from our website www.mapei.com



This symbol is used to identify Mapei products which give off a low level of volatile organic compounds (VOC) as certified by GEV (Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e.V.), an international organisation for controlling the level of emissions from products used for floors.



Our Commitment To The Environment
MAPEI products assist Project Designers and Contractors create innovative LEED (The Leadership in Energy and Environmental Design) certified projects, in compliance with the U.S. Green Building Council.

All relevant references for the product are available upon request and from www.mapei.com



BUILDING THE FUTURE